



PLASTICS

PRODUCT : ACCPLAST 90 SUPER
TYPE : 90% ALUMINA PLASTIC
NATURE OF BOND : CHEMICAL/ CERAMIC
INSTALLATION : PNEUMATIC RAMMING

GENERAL PROPERTIES

MAX. SERVICE TEMPERATURE: 1750 °C
MAXIMUM GRAIN SIZE: 4 mm
WATER CONTENT : 6.0 – 7.0 %

CHEMICAL ANALYSIS, %

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Al ₂ O ₃	86.0 – 89.0	88.55	BIS 12107 Part 3
Fe ₂ O ₃	0.20 – 0.50	0.24	BIS 12107 Part 6

PHYSICAL PROPERTIES

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Dry density, g / cc after drying at 260 °C / 3 hrs	2.68 – 2.75	2.74	BIS 10570
CCS, kg/cm ² after drying at 260 °C / 3 hrs	100 – 230	220	BIS 10570
after heating at 800 °C / 3 hrs	200 – 360	350	BIS 10570
after heating at 1550 °C / 3 hrs	250 – 450	400	BIS 10570

THERMAL PROPERTIES

	RANGE	TYPICAL VALUE	TEST PROCEDURE
Refractoriness, Orton / °C		+ 37 / + 1820	BIS 1528 Part 1
PLC, % after heating at 1550 °C / 3 hrs	+1.50 to -0.50	+1.30	BIS 10570

Delivery State: Moistened and Rammable

Storage Life: Best till 3 months from the date of production, if stored in proper condition.

Note:

(1) The data are current production averages. They can not be used as limits for specification.

AUTH. CHANNEL PARTNER - VARSHA REFRACTORIES PVT. LTD.

Address : 04, Kailash Appt. R P Road, Near D Mart, Old RTO Compound, Behind Gurudev Hotel, Kalyan (W) 421301 Tel : 0251-2314832 / 2318832 Fax : 2314831

Email : refractory9@gmail.com Website : www.varsharefractories.com